



## Material: Asoria Gold Serie: Cénit

Characteristics	Declared Value
Flexural Strength	Lower Expected Value : 6.33 MPa Mean Value : 8.70 MPa Standard Deviation : 1.50 MPa
Frost Resistance - Normal Condition	+18.45%
Frost Resistance - De-icing salts	NPD
Slipperiness - Slip Resistance	SRV-Dry : 38 & SRV-Wet : 5
Slipperiness - Skid Resistance	NPD
Abrasion Resistance	18.60 mm
Apparent Density	2.785 kg / Dm <sup>3</sup>
Open Porosity	0.39%
Water Absorption at Atmospheric Pressure	0.24%
Dangerous Substances	NPD
Thermal Shock Resistance	-0.061%
Compression Breaking Load	180 Nmm <sup>2</sup>