



Material: Alaska Blue Serie: Cénit

Characteristics	Declared Value
Flexural Strength	Lower Expected Value : 12.26 MPa Mean Value : 14.20 MPa Standard Deviation : 1.49 MPa
Frost Resistance - Normal Condition	18.40%
Frost Resistance - De-icing salts	NPD
Slipperiness - Slip Resistance	SRV-Dry : 38 & SRV-Wet : 5
Slipperiness - Skid Resistance	NPD
Abrasion Resistance	16.63 mm
Apparent Density	2.780 kg / Dm3
Open Porosity	0.38%
Water Absorption at Atmospheric Pressure	0.20%
Dangerous Substances	NPD
Thermal Shock Resistance	-0.061%
Compression Breaking Load	190 Nmm2