



Material: Cappuccino Serie: Cénit

Characteristics	Declared Value
Flexural Strength	Lower Expected Value : 6.33 MPa Mean Value : 10.40 MPa Standard Deviation : 1.48 MPa
Frost Resistance - Normal Condition	+18.46%
Frost Resistance - De-icing salts	NPD
Slipperiness - Slip Resistance	SRV-Dry : 37 & SRV-Wet : 6
Slipperiness - Skid Resistance	NPD
Abrasion Resistance	27.0 Ha
Apparent Density	2.710 kg / Dm3
Open Porosity	0.38%
Water Absorption at Atmospheric Pressure	0.16%
Dangerous Substances	NPD
Thermal Shock Resistance	-0.061%
Compression Breaking Load	134 Nmm2