



Material: Crystallato Serie: Cénit

Characteristics	Declared Value
Flexural Strength	Lower Expected Value : 14.94 MPa Mean Value : 19 MPa Standard Deviation : 1.38 MPa
Frost Resistance - Normal Condition	+18.40%
Frost Resistance - De-icing salts	NPD
Slipperiness - Slip Resistance	SRV-Dry : 39 & SRV-Wet : 6
Slipperiness - Skid Resistance	NPD
Abrasion Resistance	16.66 mm
Apparent Density	2.622 kg / Dm3
Open Porosity	0.83%
Water Absorption at Atmospheric Pressure	0.21%
Dangerous Substances	NPD
Thermal Shock Resistance	-0,061%
Compression Breaking Load	NPD