



## Material: Ghibli Gold Serie: Cénit

Characteristics	Declared Value
Flexural Strength	Lower Expected Value : 10.45 MPa Mean Value : 11.89 MPa Standard Deviation : 1.03 MPa
Frost Resistance - Normal Condition	+6.61%
Frost Resistance - De-icing salts	NPD
Slipperiness - Slip Resistance	SRV-Dry : 45 & SRV-Wet : 7
Slipperiness - Skid Resistance	NPD
Abrasion Resistance	16.50 mm
Apparent Density	2.600 kg / Dm3
Open Porosity	0.68%
Water Absorption at Atmospheric Pressure	0.34%
Dangerous Substances	NPD
Thermal Shock Resistance	-61.00%
Compression Breaking Load	100.10 Nmm2