



Material: Gold Antique Serie: Cénit

Characteristics	Declared Value
Flexural Strength	Lower Expected Value : 10.45 MPa Mean Value : 11.91 MPa Standard Deviation : 1.03 MPa
Frost Resistance - Normal Condition	6.33%
Frost Resistance - De-icing salts	NPD
Slipperiness - Slip Resistance	SRV-Dry : 47 & SRV-Wet : 8
Slipperiness - Skid Resistance	NPD
Abrasion Resistance	16.80 mm
Apparent Density	2,601 kg / Dm ³
Open Porosity	0.68%
Water Absorption at Atmospheric Pressure	0.24%
Dangerous Substances	NPD
Thermal Shock Resistance	-0.060%
Compression Breaking Load	179 Nmm ²