



Material: Kashmir White Serie: Cénit

Characteristics	Declared Value
Flexural Strength	Lower Expected Value : 10.45 MPa Mean Value : 11.90 MPa Standard Deviation : 1.03 MPa
Frost Resistance - Normal Condition	+6.30%
Frost Resistance - De-icing salts	NPD
Slipperiness - Slip Resistance	SRV-Dry : 47 & SRV-Wet : 8
Slipperiness - Skid Resistance	NPD
Abrasion Resistance	1.15 mm
Apparent Density	2.780 kg / Dm ³
Open Porosity	0.68%
Water Absorption at Atmospheric Pressure	0.34%
Dangerous Substances	NPD
Thermal Shock Resistance	-0.061%
Compression Breaking Load	174.61 Nmm ²