



Material: Kohara Serie: Cénit

Characteristics	Declared Value
Flexural Strength	Lower Expected Value : 6.33 MPa Mean Value : 8.80 MPa Standard Deviation : 1.50 MPa
Frost Resistance - Normal Condition	+6.62%
Frost Resistance - De-icing salts	NPD
Slipperiness - Slip Resistance	SRV-Dry : 47 & SRV-Wet : 8
Slipperiness - Skid Resistance	NPD
Abrasion Resistance	0.37 mm
Apparent Density	2.720 kg / Dm3
Open Porosity	0.69%
Water Absorption at Atmospheric Pressure	0.25%
Dangerous Substances	NPD
Thermal Shock Resistance	-0.06%
Compression Breaking Load	NPD