



## Material: Labradorita White Serie: Cénit

Characteristics	Declared Value
Flexural Strength	Lower Expected Value : 10.45 MPa Mean Value : 15.99 MPa Standard Deviation : 1.03 MPa
Frost Resistance - Normal Condition	6.60%
Frost Resistance - De-icing salts	NPD
Slipperiness - Slip Resistance	SRV-Dry : 46 & SRV-Wet : 7
Slipperiness - Skid Resistance	NPD
Abrasion Resistance	15.83 mm
Apparent Density	2.700 kg / Dm3
Open Porosity	0.65%
Water Absorption at Atmospheric Pressure	0.10%
Dangerous Substances	NPD
Thermal Shock Resistance	0,061%
Compression Breaking Load	135.38 Nmm2