



Material: Marine Black Serie: Cénit

Characteristics	Declared Value
Flexural Strength	Lower Expected Value : 10.45 MPa Mean Value : 11.92 MPa Standard Deviation : 1.03 MPa
Frost Resistance - Normal Condition	+18.40%
Frost Resistance - De-icing salts	NPD
Slipperiness - Slip Resistance	SRV-Dry : 39 & SRV-Wet : 6
Slipperiness - Skid Resistance	NPD
Abrasion Resistance	16.65 mm
Apparent Density	2.788 kg / Dm ³
Open Porosity	0.39%
Water Absorption at Atmospheric Pressure	0.25%
Dangerous Substances	NPD
Thermal Shock Resistance	-61.00%
Compression Breaking Load	160 Nmm ²