



Material: Premium Black Serie: Cénit

Characteristics	Declared Value
Flexural Strength	Lower Expected Value : 15.49 MPa Mean Value : 19.13 MPa Standard Deviation : 1.39 MPa
Frost Resistance - Normal Condition	+31.80%
Frost Resistance - De-icing salts	NPD
Slipperiness - Slip Resistance	SRV-Dry : 44 & SRV-Wet : 8
Slipperiness - Skid Resistance	NPD
Abrasion Resistance	15.86 mm
Apparent Density	3.050 kg / Dm ³
Open Porosity	0.27%
Water Absorption at Atmospheric Pressure	0.20%
Dangerous Substances	NPD
Thermal Shock Resistance	-0.080%
Compression Breaking Load	NPD