



Material: River White Serie: Cénit

| Characteristics | Declared Value |
|--|---|
| Flexural Strength | Lower Expected Value : 10.45 MPa Mean Value : 11.90 MPa Standard Deviation : 1.03 MPa |
| Frost Resistance - Normal Condition | +6.59% |
| Frost Resistance - De-icing salts | NPD |
| Slipperiness - Slip Resistance | SRV-Dry : 46 & SRV-Wet : 7 |
| Slipperiness - Skid Resistance | NPD |
| Abrasion Resistance | 16.83 mm |
| Apparent Density | 2.601 kg / Dm ³ |
| Open Porosity | 0.68% |
| Water Absorption at Atmospheric Pressure | 0.24% |
| Dangerous Substances | NPD |
| Thermal Shock Resistance | -0.061% |
| Compression Breaking Load | 170 Nmm ² |