



Material: Surya Serie: Cénit

Characteristics	Declared Value
Flexural Strength	Lower Expected Value : 7.47 MPa Mean Value : 10.83 MPa Standard Deviation : 1.68 MPa
Frost Resistance - Normal Condition	+6.62%
Frost Resistance - De-icing salts	NPD
Slipperiness - Slip Resistance	SRV-Dry : 47 & SRV-Wet : 8
Slipperiness - Skid Resistance	NPD
Abrasion Resistance	16.83 mm
Apparent Density	2.590 kg / Dm ³
Open Porosity	1.52%
Water Absorption at Atmospheric Pressure	0.36%
Dangerous Substances	NPD
Thermal Shock Resistance	-0.061%
Compression Breaking Load	120.21 Kg/Cm ²