



Material: Verde Marina Serie: Cénit

Characteristics	Declared Value
Flexural Strength	Lower Expected Value : 6.33 MPa Mean Value : 8.64 MPa Standard Deviation : 1.49 MPa
Frost Resistance - Normal Condition	+18.45%
Frost Resistance - De-icing salts	NPD
Slipperiness - Slip Resistance	SRV-Dry : 47 & SRV-Wet : 8
Slipperiness - Skid Resistance	NPD
Abrasion Resistance	16.64 mm
Apparent Density	2.779 kg / Dm ³
Open Porosity	0.38%
Water Absorption at Atmospheric Pressure	0.25%
Dangerous Substances	NPD
Thermal Shock Resistance	-0.061%
Compression Breaking Load	220.51 Nmm ²