



# Material: White Splendor Serie: Cénit

Characteristics	Declared Value
Flexural Strength	Lower Expected Value : 14.90 MPa Mean Value : 18.00 MPa Standard Deviation : 1.68 MPa
Frost Resistance - Normal Condition	+18.40%
Frost Resistance - De-icing salts	NPD
Slipperiness - Slip Resistance	SRV-Dry : 39 & SRV-Wet : 6
Slipperiness - Skid Resistance	NPD
Abrasion Resistance	16.60 mm
Apparent Density	2.615 kg / Dm <sup>3</sup>
Open Porosity	0.83%
Water Absorption at Atmospheric Pressure	0.21%
Dangerous Substances	NPD
Thermal Shock Resistance	-61.00%
Compression Breaking Load	170 Nmm <sup>2</sup>